

Product and Application

TruSTRENGTH 100 QT plate provides excellent properties in strength and toughness. This quenched and tempered product excels in downstream fabrication processes like bending, machining laser cutting, plasma cutting and welding. This product is used widely in construction and forestry equipment, mining, cranes, heavy-duty transport equipment, railcars and various applications requiring a high strength-to-weight ratio.

Available in thicknesses up to 0.500", widths up to 60" and lengths up to 288".

Mechanical Properties

Yield Strength (min.)	100 ksi (689 MPa)
Tensile Strength (min.)	110 ksi (758 MPa)
Elongation	18%
Reduction of Area	60%
Charpy V-Notch @ -40° F	60 ft-lbs (81.3 J) longitudinal, 50 ft-lbs (67.8 J) transverse
Charpy V-Notch @ -40° F (min.)	30 ft-lbs (40.7 J) transverse
Bend Radius	1.5T (longitudinal), 2T (transverse). Larger bend radius recommended for thicker plates.

Typical values unless otherwise noted.

Different Charpy Impact test temperatures may be specified, with mechanical tests conducted in accordance with ASTM A370, latest revision.

Tensile and Charpy Impact tests conducted per heat/heat treat lot. Hardness also taken on each plate, but not reported.

Dimensional Tolerances

Flatness Flatness tolerances meet 1/2 of ASTM A6, Table 14, latest revision. TruFLAT tolerance of 1/4 ASTM A6 for 0.300" and thinner.

TRUFLAT[™]

Thickness +/- 0.012" to nominal thickness

Length and Width Length and width tolerances meet ASTM A6, latest revision

Chemical Composition

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
Max	0.24	1.60	0.020	0.015	0.34	0.25	0.45	0.65	0.30
CEV (typical):			0.58	CEV = C + Mn/6 + (Cr+Mo+V)/5 + (Ni+Cu)/15					
CET (typical):			0.40	CET=C + (Mn+Mo)/10 + (Cr+Cu)/20 + Ni/40					
CEq (typical):			0.39	CEq= C + Si/25 + (Mn+Cu)/16 + Ni/40 + Cr/10 + Mo/15 + V/10					

Fabrication, Bending, Post-Delivery Heating and Welding

Bending	Free bending should be performed utilizing maximum allowable bend radius to prevent cracking. TruSTRENGTH 100 QT plates can be bent using a minimum radius of 1.5T in the longitudinal direction and 2T in the transverse direction. Larger bend radius is recommended for thicker plates. Transverse radius is the bend line parallel to rolling direction.
Welding	TruSTRENGTH 100 QT plate can be welded by conventional processes such as SMAW, SAW and GMAW, provided that the weld procedures used are suitable for this grade and design of the welded structure, using low hydrogen conditions.

*These statements are general guidelines. CMC Impact Metals is not responsible for the results of any welding work performed.

Standard Delivery Conditions

Surface Finish	Shot blasting and rust preventative applications are available. Please inquire.
Test Reports	Supplied with shipment for each production lot in the shipment. Reports include product description, heat number, chemical analysis and Brinell hardness value.